

NOVASIT BM

Fire protection mortar

Description

Fibre-free special mortar with particularly high adhesive strength, stability and low demands to formwork. NOVASIT BM has been in use worldwide for over 30 years.

Areas of Application

- For closing cable, pipe and mixed penetration seals.
- Application in plasterboard walls, solid walls and floors.



Delivery and Packaging

| NOVASIT BM | | |
|----------------|----------|----------|
| Packaging | bag | pail |
| Container size | 20 kg | 10 kg |
| Item number | | |
| | 01161000 | 01161010 |



NOVASIT BM

Technical Data

| B | NOVACIT DAA': 1 'C 1 AA': "II EN AGEGA A | |
|-----------------------------|---|--|
| Reaction to fire | NOVASIT BM is classified as A1 in acc. with EN 13501-1. | |
| Colour | cement grey | |
| Bulk density (fresh mortar) | 1200 ± 100 kg/m ³ | |
| Dry bulk density | ≥ 900 kg/m³ | |
| Compressive strength | M 2.5 | |
| Application temperature | ≥ +5 °C | |
| Processing time | approx. 2–3 hours | |
| Application time | after approx. 28 days | |
| Usage category | Typ Z ₂ in acc. with EOTA TR024 | |
| Application instructions | Surfaces must be solid, free of adhesion-reducing substances and dust. Absorbent surfaces should be pre-wet with water. The consistency of the mortar must be adapted to fill all necessary building elements without cavities. | |
| Consumption | 6–7 I water + 20 kg dry mortar ≈ 20 I ready-to-use wet mortar ≈ 20 I volume after hardening | |

| Storage | Cool and dry. Can remain unopened for at least 12 months if stored properly. |
|--------------------------------------|--|
| Safety information | Please observe the safety data sheet. |
| Declaration of performance (DOP) no. | 01161000-NOVASIT-BM |